

Application Instructions

SKN20 Bucket

General Approximate Coverage
approx. 1L = 1 sq.metre

PREPARATION

Metal surfaces should be clean, dry and free from any existing coatings, oils, chemicals, dust or other contaminants.

APPLICATION

Before use, stir thoroughly for up to 5 mins using a stirring stick, stir periodically during use.

Using a brush or roller, apply the coating thickly and evenly across the surface.

- Single Coat thickness 200-250 um DFT, with 2-3 coats being recommended.
- The thicker the coating the easier the peel.
- Touch dry in 8-10 minutes
- Ready to handle in 30 minutes
- Cured in 24 hours
- Ultimate storage and application temperature is between 20° C and 38°C.

Reorder code: 04-SKN20/4



© Omni-tuff Group Pty Ltd t/a DAYWALK

DISCLAIMER: While all effort has been made to represent the products accurately, details may vary due to photography and videography processes. The customer will make their own assessment as to the suitability of the products for the customer's purposes. The actual use of the product is within the sole control of the customer and DAYWALK will not be responsible for such loss or damage resulting from such use. Sales are subject to standard terms and conditions of trade of DAYWALK. E&OE