

# Application Instructions

## SKN45 Aerosol

### PREPARATION

Metal surfaces should be clean, dry and free from any existing coatings, oils, chemicals, dust or other contaminants.

### APPLICATION

Cover surrounding surfaces to protect from any unwanted over spray.

Before use, shake vigorously for up to 5 mins; shake periodically during use.

Spray in an even motion, holding the can at least 200mm from the metal surface you are spraying.

Make the first coat thin but consistent: this makes a good tack coat foundation for subsequent coats

- Single Coat thickness – 100-150 um DFT, with 2-3 coats being recommended.
- For best effect spray evenly and quickly to achieve optimum hold.
- Touch dry in 2-5 minutes
- Ready to handle in 10 minutes
- Cured in 24 hours
- Once you have finished application, invert the can and spray to clear excess paint from nozzle.
- Ultimate storage and application temperature is between 20°) and 38°C.

**Reorder code: 04-SKN45/AERO380**



© Omni-tuff Group Pty Ltd t/a DAYWALK

DISCLAIMER: While all effort has been made to represent the products accurately, details may vary due to photography and videography processes. The customer will make their own assessment as to the suitability of the products for the customer's purposes. The actual use of the product is within the sole control of the customer and DAYWALK will not be responsible for such loss or damage resulting from such use. Sales are subject to standard terms and conditions of trade of DAYWALK. E&OE